



Product/Service Information

NAS-HVC High Velocity Compound for Masking

NAS-HVC is a 2-component Room temperature addition curing kneadable Silicone.

Halogen and Chloride free suitable for Aviation Application on Approval.

Processing: Take two equal-size amounts of components A and B and knead them manually until a homogenous colour develops.

Processing time: 90 seconds (this could be extended on Customer feedback)

Curing time: approx: 5 minutes

NAS-HVC operating temperature is up to 300 Deg. C.

Hardness: 70 Shore A deg.

Colour: White and grey. (this could be changed after Customer trials)

Application: HVOF

Shelf life: 6 months

Packaging size: 0.5 Kg, 1.0Kg, 1.5Kg, 2.0Kg, 50% each of A+B.