

P♦MET 714 Arc Spray Wire

DESCRIPTION

P♦Met 714 is a high carbon steel wire specifically designed for arc spraying. It produces dense, well-bonded coatings with excellent wear resistance, and is widely used for machine element repair, dimensional restoration and wear resistant applications. **P♦Met 714** low shrink characteristics allow for increased coating thickness.

TYPICAL DEPOSIT CHARACTERISTICS:

- Typical Hardness HRC 20-25
- Bond Strength 4800 psi
- Deposit Rate 10 lbs /hr/100A
- Deposit Efficiency 70%
- Wire Coverage 0.8 oz/ft² / m
- Surface Texture *Variable
- Machineability Good

* Depends on air pressure used.

SURFACE PREPARATION:

Surface should be clean, white metal, with no oxides (rust), dirt, grease, or oil on the surface to be coated. **Note:** It is best not to handle surfaces after cleaning. Recommended method of preparation is, to grit blast with 24 mesh aluminum oxide, rough grind, or rough machine in a lathe.

APPLICATION:

- Part Restoration
- Seating Surfaces
- Press Fit Surfaces

SPECIFICATION:

High Carbon Steel Wire

NOMINAL CHEMICAL COMPOSITION (wt%):

C	Mn	Si	Fe
0.8	0.7	0.3	Bal

RECOMMENDED SPRAY PARAMETERS:

Diameter	Air Pressure	Voltage	Amperage	Standoff
1/16" (1.6mm)	*50 - 60 psi	*28 - 30	*100 - 300	*4 - 6 in (10 - 15cm)

* Parameters are typical and may vary depending on equipment used. Contact your equipment manufacture for optimum spray parameters.

STANDARD SIZES & PACKAGING:

Diameter	Packaging	Part Number
1/16 (1.6mm)	25# LLWS	714062LWS01

The properties listed are typical and not to be construed as guaranteed values. Actual properties may vary depending on customer operating conditions. Polymet makes no warranties, express or implied, including, but not limited to, the implied warranties of merchantability and fitness for a particular purpose, except as expressly stated in Polymet's terms and conditions.